

Nylamid® 9110 G40 BK

TECHNICAL DATASHEET

TDS Ref # 762 Reviewed: 10/18/2013

DESCRIPTION

• Nylamid 9110 G40 BK is a 40% glass fiber-reinforced nylon 6/10 molding resin offering the good strength properties expected from glass filled materials.

PROPERTIES	TEST METHOD	UNIT	VALUE
PHYSICAL PROPERTIES			
Specific Gravity	D792	n/a	1.46
MECHANICAL PROPERTIES			
Elongation @ Break	D638	[%]	3
Flexural Modulus	D790	psi (MPa)	1,420,000 (9,760)
Notched Izod @ 23°C	D256	ftlb/in (J/m)	2.3 (125)
Tensile Modulus	D638	psi (MPa)	1,540,000 (10,600)
Tensile Strength	D638	psi (MPa)	21,600 (149)
THERMAL PROPERTIES			
DTUL @ 1820 kPa	D648	°F (°C)	207 (406)
Melt Point	D3418	°F (°C)	415 (213)

NOTES

• Testing conducted on dry-as-molded specimens at 73°F

PROCESSING CONSIDERATIONS: SPECIALTY SPECIALTY 6/10

Please contact for processing information on this product.

CHARACTERISTICS

Resin Type: Nylon 6/10
Product Characteristics:
Glass Reinforced, Copolymer

INJECTION MOLDING PROCESSING

Specialty Grade

FEATURES

- Nylene 9110 G40 BK offers good strength properties expected from glass filled materials.
- Higher stiffness
- Low moisture

MARKETS USED

- Tool & Appliance

APPLICATIONS

- Water Pump

DISCLAIMER

The data set forth herein has been carefully compiled by Nylene in our laboratories. Values shown are typical properties and not specifications. Since processing variables will affect properties, the reproducibility of our data in a customer's testing facility is not guaranteed. There is no warranty of any kind, either expressed or implied, applicable to the use of this information, and the user assumes all risk and liability in connection therewith.



Headquarters and Facility:
55 Haul Road, Wayne, NJ 07470
P: 973-694-4141 | F: 973-694-3549

North American Sales Office:
31700 Telegraph Rd. Suite 235, MI 48025
P: 248-377-6769 | F: 248-377-3845

Nylene Custom Resins Facility:
1421 Hwy 136 W. Henderson, KY 42420
P: 270-826-7641 | TF: 800-626-7050

Nylene Canada Facility
200 McNab Street, Arnprior ON, K7S 3P2
P: 613-623-3191 | TF: 800-267-7394

For a complete listing of our global offices, visit:
www.nylene.com/contactus
www.nylene.com | info@nylene.com

Copyright ©2019, Nylene. All rights reserved. Nylene is a designated trademark of Polymeric Resources Corporation.