

# Nylene® 201 MS3

## TECHNICAL DATASHEET

TDS Ref # 951 Reviewed: 8/1/2017

### DESCRIPTION

- Nylene 201 MS3 is a molybdenum disulfide lubricated nylon 6 molding resin with high ductility.
- Optimum processing conditions should provide a melt temperature of 430 - 480 °F at the nozzle.
- The abrasion resistance of nylon is enhanced by the addition of molybdenum disulfide.
- Excellent wear properties

PROPERTIES	TEST METHOD	UNIT	VALUE
<b>MECHANICAL PROPERTIES</b>			
Elongation	D638	%	50
Flexural Modulus	D790	psi (MPa)	340,000 [2,340]
Notched Izod @ 23°C	D256	ft. lb./ in. (J/m)	2.0 (105)
Tensile Strength	D638	psi (MPa)	9,070 [62]
<b>THERMAL PROPERTIES</b>			
Melt Point (DSC)	ASTM D3418	°C	223

### NOTES

- Testing conducted on dry-as-molded specimens at 73°F (23°C)

### PROCESSING CONSIDERATIONS: PA 6 UNREINFORCED

°F (°C)	Rear Zone	430-475 (221-249)	<p><b>Melt Temperature:</b> Melt Temperature: Nylene® PA6 melts at 428°F, (220°C) actual melt temperatures of 440-560°F (227-293°C) are permissible, depending on residence time and shot size.</p> <p><b>Mold Temperature:</b> 120-200°F (49-93°C), highly filled grades require 180-200°F (82-93°C) to obtain the best overall surface appearance, higher temperatures will increase crystallinity.</p> <p><b>Residence Time:</b> should not exceed 6 minutes if possible, less with higher melt temperatures</p> <p><b>Shot Size:</b> should be between 25-75% of barrel capacity.</p> <p><b>Fill Rate:</b> fast fill rates are suggested for best surface appearance.</p> <p><b>Regrind Level:</b> typically no more than 25% is recommended, with higher levels possible for unfilled grades depending on the end use requirements. Make certain regrind is properly dried to virgin moisture levels.</p> <p><b>Drying Temperature:</b> 150-180°F (66-82°C) for 2-4 hours, Nylene® PA6 should be dried to less than 0.20% moisture for optimum performance. Drying longer than 4 hours or at higher temperatures may cause discoloration of the polymer or adversely affect important physical properties.</p>
	Center Zone	440-500 (227-260)	
	Front Zone	460-520 (238-271)	
	Nozzel	460-520 (238-271)	
	Melt Temp.	460-520 (238-271)	
PRESSURE	Injection	4-12,000	
	Hold	3-9,000	
	Back	0-50	

### CHARACTERISTICS

Resin Type: Nylon 6  
 Product Characteristics:  
 Molybdenum Disulphide Lubricated,  
 High RV

### COMPOUNDING PROCESSING

Prime Grade

### INJECTION MOLDING PROCESSING

Prime Grade

### FEATURES

- Contains molybdenum disulfide

### DISCLAIMER

The data set forth herein has been carefully compiled by Nylene in our laboratories. Values shown are typical properties and not specifications. Since processing variables will affect properties, the reproducibility of our data in a customer's testing facility is not guaranteed. There is no warranty of any kind, either expressed or implied, applicable to the use of this information, and the user assumes all risk and liability in connection therewith.



**Headquarters and Facility:**  
 55 Haul Road, Wayne, NJ 07470  
 P: 973-694-4141 | F: 973-694-3549

**North American Sales Office:**  
 31700 Telegraph Rd. Suite 235, MI 48025  
 P: 248-377-6769 | F: 248-377-3845

**Nylene Custom Resins Facility:**  
 1421 Hwy 136 W. Henderson, KY 42420  
 P: 270-826-7641 | TF: 800-626-7050

**Nylene Canada Facility**  
 200 McNab Street, Arnprior ON, K7S 3P2  
 P: 613-623-3191 | TF: 800-267-7394

For a complete listing of our global offices, visit:  
[www.nylene.com/contactus](http://www.nylene.com/contactus)  
[www.nylene.com](http://www.nylene.com) | [info@nylene.com](mailto:info@nylene.com)

Copyright ©2019, Nylene. All rights reserved. Nylene is a designated trademark of Polymeric Resources Corporation.