

Nylene® 2407 HSSP BK

TECHNICAL DATASHEET

TDS Ref # 748 Reviewed: 7/15/2013

DESCRIPTION

- High viscosity nylon copolymer with high impact resistance and superior flexibility
- Optimized with good melt strength for high line speeds in thin wall sections, and is available in natural and black
- 2407 HSSP is one of a family of grades specifically designed for the convoluted tubing industry, but can also be used for other extrusions and some molded parts
- Very good physical properties and excellent extrusion characteristics to support extrusion of very complex profiles.

PROPERTIES	TEST METHOD	UNIT	VALUE
PHYSICAL PROPERTIES			
Specific Gravity	D792	n/a	1.07
MECHANICAL PROPERTIES			
Flexural Modulus	D790	psi (MPa)	86,100 (595)
Notched Izod @ 23°C	D256	ftlb/in (J/m)	10.7 (541)
Tensile Modulus	D638	psi (MPa)	123,000 (858)
Tensile Strength	D638	psi (MPa)	6,550 (45)
THERMAL PROPERTIES			
DTUL @ 455 KPa	D648	°F (°C)	162 (323)
Melt Flow	D1238	dg/min	1.7
Melt Point	D3418	°F (°C)	424 (218)

NOTES

- Testing conducted on dry-as-molded specimens at 73°F

PROCESSING CONSIDERATIONS: EXTRUSION PLASTICIZED

Zone °F (°C)	Feed	420-440 (216-227)	Residence Time: Screw should not be left idle for more than 3-4 minutes with melt in the barrel. Excess residence will be visible as black carbon specs in the melt.
	Transition	440-460 (227-238)	Regrind Level: Typically, up to 25% is recommended but higher levels are possible with little or no effect on flow and finish.
	Metering	450-470 (232-243)	Drying Temperature: Although Nylene resins are packaged and delivered in a low moisture state, it is good material handling practice to use a hopper dryer to maintain dryness. Should pre-drying be necessary, use settings of 180 °F (82.2°C) air at dew point of -40 at a rate of 1 cu. ft. / hour per pound of resin and a residence time of 2-4 hours.
	Die	450-470 (232-243)	
	Melt Temp.	450-470 (232-243)	Cooling and Sizing: While both air and water can be used as the cooling medium, air is preferred. The use of air allows additional time for sizing and reduces residual stress. This aids in reducing warpage, especially in profiles with varying wall sections. If water is used, heat the first section to above 100 °F (38°C) to reduce quenching and residual stress.
Line Rate	2 ½" extruder	1.5 - 1.9 pph/rpm	
	3 ½" extruder	3.5 - 4.5 pph/rpm	Die Design: Draw down of 30% is typical for all dimensions except wall thickness.
	4 ½" extruder	6.5 - 7.5 pph/rpm	Land length: should be around 10x wall thickness.

CHARACTERISTICS

Resin Type: Nylon 6
 Product Characteristics:
 Unreinforced, Copolymer, High RV

EXTRUSION PROCESSING

Tubing & Profile

FEATURES

- Superior flexibility
- Used for other extrusions & molded parts
- Low cost, heat resistance
- High viscosity
- High impact resistance
- Available in natural or black

MARKETS USED

- Automotive Applications
- Tool & Appliance
- Lawn and Garden
- Convoluted Tubing Industry

APPLICATIONS

- Convoluted Tubing

AUTOMOTIVE SPECIFICATION

- GMP.PA6.003

DISCLAIMER

The data set forth herein has been carefully compiled by Nylene in our laboratories. Values shown are typical properties and not specifications. Since processing variables will affect properties, the reproducibility of our data in a customer's testing facility is not guaranteed. There is no warranty of any kind, either expressed or implied, applicable to the use of this information, and the user assumes all risk and liability in connection therewith.



Headquarters and Facility:
 55 Haul Road, Wayne, NJ 07470
 P: 973-694-4141 | F: 973-694-3549

North American Sales Office:
 31700 Telegraph Rd. Suite 235, MI 48025
 P: 248-377-6769 | F: 248-377-3845

Nylene Custom Resins Facility:
 1421 Hwy 136 W. Henderson, KY 42420
 P: 270-826-7641 | TF: 800-626-7050

Nylene Canada Facility
 200 McNab Street, Arnprior ON, K7S 3P2
 P: 613-623-3191 | TF: 800-267-7394

For a complete listing of our global offices, visit:
www.nylene.com/contactus
www.nylene.com | info@nylene.com

Copyright ©2019, Nylene. All rights reserved. Nylene is a designated trademark of Polymeric Resources Corporation.