

Nylene® 2407 HSSP

TECHNICAL DATASHEET

TDS Ref # 72 Reviewed: 7/15/2013

DESCRIPTION

- High viscosity nylon copolymer with high impact resistance and superior flexibility
- Optimized with good melt strength for high line speeds in thin wall sections, and is available in natural and black
- One of a family of grades specifically designed for the convoluted tubing industry, but can also be used for other extrusions and some molded parts.

PROPERTIES	TEST METHOD	UNIT	VALUE
PHYSICAL PROPERTIES			
Linear Mold Shrinkage		cm/cm (in/in)	0.0120 (0.0120)*
Specific Gravity	D792	n/a	1.07
MECHANICAL PROPERTIES			
Elongation	D638	%	250
Flexural Modulus	D790	psi (MPa)	86,100 (595)
Tensile Strength	D638	psi (MPa)	6,500 (45)
THERMAL PROPERTIES			
DTUL @ 1800 kPa	ISO 75	°C (°F)	43 (27)
DTUL @ 455 KPa	D648	°F (°C)	323 (162)
Melt Flow	D1238	dg/min	1.7
Melt Point	D3418	°F (°C)	424 (218)

NOTES

- Testing conducted on dry-as-molded specimens at 73°F (23°C)
- Linear Mold Shrinkage value is conditioned

PROCESSING CONSIDERATIONS: EXTRUSION HIGH VISCOSITY

Zone °F (°C)	Feed	500-530 (260-277)	Residence Time: Screw should not be left idle for more than 3-4 minutes with melt in the barrel. Excess residence will be visible as black carbon specs in the melt.
	Transition	520-560 (271-293)	Regrind Level: Typically, up to 25% is recommended but higher levels are possible with little or no effect on flow and finish.
	Metering	550-575 (288-302)	Drying Temperature: Although Nylene resins are packaged and delivered in a low moisture state, it is good material handling practice to use a hopper dryer to maintain dryness. Should pre-drying be necessary, use settings of 180 °F (82.2°C) air at dew point of -40 at a rate of 1 cu. ft. / hour per pound of resin and a residence time of 2-4 hours.
	Die	550-575 (288-302)	
	Melt Temp.	550-575 (288-302)	Cooling and Sizing: While both air and water can be used as the cooling medium, air is preferred. The use of air allows additional time for sizing and reduces residual stress. This aids in reducing warpage, especially in profiles with varying wall sections. If water is used, heat the first section to above 100 °F (38°C) to reduce quenching and residual stress.
Line Rate	2 ½" extruder	1.5 - 1.9 pph/rpm	
	3 ½" extruder	3.5 - 4.5 pph/rpm	Die Design: Draw down of 30% is typical for all dimensions except wall thickness.
	4 ½" extruder	6.5 - 7.5 pph/rpm	Land length: should be around 10x wall thickness.

CHARACTERISTICS

Resin Type: Nylon 6
 Product Characteristics:
 High Impact, Flex Modified, High RV

EXTRUSION PROCESSING

Tubing & Profile

INJECTION MOLDING PROCESSING

Prime Grade

MARKETS USED

- Automotive Applications
- Convoluted Tubing Industry

APPLICATIONS

- Convoluted Tubing

APPROVALS

- FMVSS 302: 3.47 in/min (88.1 mm/min)

DISCLAIMER

The data set forth herein has been carefully compiled by Nylene in our laboratories. Values shown are typical properties and not specifications. Since processing variables will affect properties, the reproducibility of our data in a customer's testing facility is not guaranteed. There is no warranty of any kind, either expressed or implied, applicable to the use of this information, and the user assumes all risk and liability in connection therewith.



Headquarters and Facility:

55 Haul Road, Wayne, NJ 07470
 P: 973-694-4141 | F: 973-694-3549

North American Sales Office:

31700 Telegraph Rd. Suite 235, MI 48025
 P: 248-377-6769 | F: 248-377-3845

Nylene Custom Resins Facility:

1421 Hwy 136 W. Henderson, KY 42420
 P: 270-826-7641 | TF: 800-626-7050

Nylene Canada Facility

200 McNab Street, Arnprior ON, K7S 3P2
 P: 613-623-3191 | TF: 800-267-7394

For a complete listing of our global offices, visit:

www.nylene.com/contactus

www.nylene.com | info@nylene.com

Copyright ©2019, Nylene. All rights reserved. Nylene is a designated trademark of Polymeric Resources Corporation.