

Nylene® 2408 HSSP UV

TECHNICAL DATASHEET

TDS Ref # 977 Reviewed: 2/13/2018

DESCRIPTION

- Nylene 2408 HSSP UV is a modified nylon 6 with very good physical properties and excellent extrusion characteristics to support extrusion of very complex profiles. Especially useful for convoluted tubing.
- Resistance to UV light.

PROPERTIES	TEST METHOD	UNIT	VALUE
PHYSICAL PROPERTIES			
Density	ISO 1183	g/cm ³	1.07
MECHANICAL PROPERTIES			
Elongation @ Break	ISO 527	(%)	70
Flexural Modulus	ISO 178	MPa	1710
Notched Izod @ 23°C	ISO 180	kJ/m ²	100
Tensile Strength	ISO 527	MPa	51
THERMAL PROPERTIES			
Melt Point	ISO 11357	°C (°F)	246 (475)

NOTES

- Testing conducted on dry-as-molded specimens at 73°F

PROCESSING CONSIDERATIONS: EXTRUSION IMPACT MODIFIED

Zone °F (°C)	Feed	450-470 (232-243)	Residence Time: Screw should not be left idle for more than 3-4 minutes with melt in the barrel. Excess residence will be visible as black carbon specs in the melt.
	Transition	470-500 (243-260)	Regrind Level: Typically, up to 25% is recommended but higher levels are possible with little or no effect on flow and finish.
	Metering	490-530 (254-277)	Drying Temperature: Although Nylene resins are packaged and delivered in a low moisture state, it is good material handling practice to use a hopper dryer to maintain dryness. Should pre-drying be necessary, use settings of 180 °F (82.2°C) air at dew point of -40 at a rate of 1 cu. ft. / hour per pound of resin and a residence time of 2-4 hours.
	Die	490-530 (254-277)	
	Melt Temp.	490-530 (254-277)	Cooling and Sizing: While both air and water can be used as the cooling medium, air is preferred. The use of air allows additional time for sizing and reduces residual stress. This aids in reducing warp, especially in profiles with varying wall sections. If water is used, heat the first section to above 100 °F (38°C) to reduce quenching and residual stress.
Line Rate	2 ½" extruder	1.5 - 1.9 pph/rpm	Die Design: Draw down of 30% is typical for all dimensions except wall thickness. Land length: should be around 10x wall thickness.
	3 ½" extruder	3.5 - 4.5 pph/rpm	
	4 ½" extruder	6.5 - 7.5 pph/rpm	

CHARACTERISTICS

Resin Type: Nylon 6
Product Characteristics:
Heat Stabilized, UV Stabilized

EXTRUSION PROCESSING

Tubing & Profile

DISCLAIMER

The data set forth herein has been carefully compiled by Nylene in our laboratories. Values shown are typical properties and not specifications. Since processing variables will affect properties, the reproducibility of our data in a customer's testing facility is not guaranteed. There is no warranty of any kind, either expressed or implied, applicable to the use of this information, and the user assumes all risk and liability in connection therewith.



Headquarters and Facility:

55 Haul Road, Wayne, NJ 07470
P: 973-694-4141 | F: 973-694-3549

North American Sales Office:

31700 Telegraph Rd. Suite 235, MI 48025
P: 248-377-6769 | F: 248-377-3845

Nylene Custom Resins Facility:

1421 Hwy 136 W. Henderson, KY 42420
P: 270-826-7641 | TF: 800-626-7050

Nylene Canada Facility

200 McNab Street, Arnprior ON, K7S 3P2
P: 613-623-3191 | TF: 800-267-7394

For a complete listing of our global offices, visit:

www.nylene.com/contactus

www.nylene.com | info@nylene.com

Copyright ©2019, Nylene. All rights reserved. Nylene is a designated trademark of Polymeric Resources Corporation.