

# Nylene® 4114 UV

## TECHNICAL DATASHEET

TDS Ref # 961 Reviewed: 12/12/2017

### DESCRIPTION

- Impact-modified nylon 6,6 compounded copolymer, high melt point and increased flexibility.
- Light stabilized for **UV protection**

PROPERTIES	TEST METHOD	UNIT	VALUE
<b>PHYSICAL PROPERTIES</b>			
Mold Shrinkage	n/a	in/in	0.014
Specific Gravity	D792	n/a	1.07
<b>MECHANICAL PROPERTIES</b>			
Elongation @ Break	D638	[%]	60
Flexural Modulus	D790	psi (MPa)	233,000 [1,600]
Notched Izod @ 23°C	D256	ft. lb./ in. (J/m)	16 [850]
Tensile Modulus	D638	psi (MPa)	254,000 [1750]
Tensile Strength	D638	psi (MPa)	6,520 [45]
<b>THERMAL PROPERTIES</b>			
DTUL @ 1820 kPa	D648	°F (°C)	135 [57]
Melt Point	D3418	°F (°C)	500 [260]

### NOTES

- Testing conducted on dry-as-molded specimens at 73°F

### PROCESSING CONSIDERATIONS: PA 6/6 IMPACT MODIFIED

°F (°C)	Rear Zone	500-540 (260-282)	<b>Melt Temperature:</b> Nylene® PA6/6 melts at 490 °F (254°C), actual melt temperatures of 540-600 (282-316°C) are permissible, depending on residence time and shot size.
	Center Zone	520-560 (271-293)	<b>Mold Temperature:</b> 120-200 °F (49-93°C), highly filled grades require 180-200 °F (82-93°C) to obtain the best overall surface appearance, higher temperatures will increase crystallinity.
	Front Zone	540-580 (282-304)	<b>Residence Time:</b> should not exceed 6 minutes if possible, less with higher melt temperatures.
	Nozzel	535-575 (279-301)	<b>Shot Size:</b> should be between 25-75% of barrel capacity.
	Melt Temp.	540-580 (282-304)	<b>Fill Rate:</b> fast fill rates are suggested for best surface appearance.
PRESSURE	Injection	7-15,000	<b>Regrind Level:</b> typically no more than 25% is recommended, with higher levels possible for unfilled grades depending on the end use requirements. Make certain regrind is properly dried to virgin moisture levels.
	Hold	5-12,000	<b>Drying Temperature:</b> 150-180 °F (65-82°C) for 2-4 hours, Nylene® PA6/6 should be dried to less than 0.20% moisture for optimum performance. Drying longer than 4 hours or at higher temperatures may cause oxidation of the polymer or remove essential volatiles.
	Back	0-50	

### CHARACTERISTICS

Resin Type: Nylon 6/6  
 Product Characteristics:  
 Impact Modified, UVStabilized,  
 Compounded Copolymer

### INJECTION MOLDING PROCESSING

Prime Grade

### FEATURES

- High impact resistant
- Most flexible
- Wear resistant
- UV Protection

### MARKETS USED

- Automotive Applications
- General Applications
- Industrial Applications

### APPLICATIONS

- Clips
- Conveyor Lever
- Engine Cover
- Fasteners
- Headrest Guide
- Seat Adjuster Levers
- Seat Belt Components
- Seat Pan

### DISCLAIMER

The data set forth herein has been carefully compiled by Nylene in our laboratories. Values shown are typical properties and not specifications. Since processing variables will affect properties, the reproducibility of our data in a customer's testing facility is not guaranteed. There is no warranty of any kind, either expressed or implied, applicable to the use of this information, and the user assumes all risk and liability in connection therewith.



#### Headquarters and Facility:

55 Haul Road, Wayne, NJ 07470  
 P: 973-694-4141 | F: 973-694-3549

#### North American Sales Office:

31700 Telegraph Rd. Suite 235, MI 48025  
 P: 248-377-6769 | F: 248-377-3845

#### Nylene Custom Resins Facility:

1421 Hwy 136 W. Henderson, KY 42420  
 P: 270-826-7641 | TF: 800-626-7050

#### Nylene Canada Facility

200 McNab Street, Arnprior ON, K7S 3P2  
 P: 613-623-3191 | TF: 800-267-7394

For a complete listing of our global offices, visit:

[www.nylene.com/contactus](http://www.nylene.com/contactus)

[www.nylene.com](http://www.nylene.com) | [info@nylene.com](mailto:info@nylene.com)

Copyright © 2019, Nylene. All rights reserved. Nylene is a designated trademark of Polymeric Resources Corporation.