

# Nylene® 9110 G43

## TECHNICAL DATASHEET

TDS Ref # 165 Reviewed: 10/18/2013

### DESCRIPTION

- 43% glass fiber reinforced nylon 6/10 injection molding grade.
- Has the high strength and stiffness of reinforced nylon, while also having the reduced moisture pick-up associated with nylon 6/10.
- Suitable for applications where moisture pickup may be a concern.

PROPERTIES	TEST METHOD	UNIT	VALUE
<b>PHYSICAL PROPERTIES</b>			
Specific Gravity	D792	n/a	1.42
<b>MECHANICAL PROPERTIES</b>			
Elongation	D638	%	20
Flexural Modulus	D790	psi (MPa)	1,500,000 (10,345)
Notched Izod	D256	ft.Lb/in.	3.0 (160)
Tensile Strength	D638	psi (MPa)	24,000 (166)
<b>THERMAL PROPERTIES</b>			
DTUL @ 264 psi/1.82 MPa	D648	°F (°C)	398 (203)
Melt Point	D3418	°F (°C)	430 (221)

### NOTES

- Testing conducted on dry-as-molded specimens at 73°F

### PROCESSING CONSIDERATIONS: PA 6/6 GLASS REINFORCED > 15%

°F (°C)	Rear Zone	500-560 (260-293)	<b>Melt Temperature:</b> Nylene PA6/6 melts at 490 °F (254°C), actual melt temperatures of 540-600 (282-316°C) are permissible, depending on residence time and shot size.
	Center Zone	530-570 (277-299)	<b>Mold Temperature:</b> 120-200 °F (49-93°C), highly filled grades require 180-200 °F (82-93°C) to obtain the best overall surface appearance, higher temperatures will increase crystallinity.
	Front Zone	540-590 (282-310)	<b>Residence Time:</b> should not exceed 6 minutes if possible, less with higher melt temperatures.
	Nozzel	535-585 (279-307)	<b>Shot Size:</b> should be between 25-75% of barrel capacity.
	Melt Temp.	550-600 (287-316)	<b>Fill Rate:</b> fast fill rates are suggested for best surface appearance.
PRESSURE	Injection	5-15,000	<b>Regrind Level:</b> typically no more than 25% is recommended, with higher levels possible for unfilled grades depending on the end use requirements. Make certain regrind is properly dried to virgin moisture levels.
	Hold	4-12,000	<b>Drying Temperature:</b> 150-180 °F (65-182°C) (for 2-4 hours, Nylene PA6/6 should be dried to less than 0.20% moisture for optimum performance. Drying longer than 4 hours or at higher temperatures may cause oxidation of the polymer or remove essential volatiles.
	Back	0-50	

### CHARACTERISTICS

Resin Type: Nylon 6/6  
 Product Characteristics:  
 Glass Reinforced, Copolymer

### INJECTION MOLDING PROCESSING

Prime Grade

### MARKETS USED

- General Applications

### APPLICATIONS

- Fasteners
- Inlet Housings
- Pump Housings

### DISCLAIMER

The data set forth herein has been carefully compiled by Nylene in our laboratories. Values shown are typical properties and not specifications. Since processing variables will affect properties, the reproducibility of our data in a customer's testing facility is not guaranteed. There is no warranty of any kind, either expressed or implied, applicable to the use of this information, and the user assumes all risk and liability in connection therewith.



#### Headquarters and Facility:

55 Haul Road, Wayne, NJ 07470  
 P: 973-694-4141 | F: 973-694-3549

#### North American Sales Office:

31700 Telegraph Rd. Suite 235, MI 48025  
 P: 248-377-6769 | F: 248-377-3845

#### Nylene Custom Resins Facility:

1421 Hwy 136 W. Henderson, KY 42420  
 P: 270-826-7641 | TF: 800-626-7050

#### Nylene Canada Facility

200 McNab Street, Arnprior ON, K7S 3P2  
 P: 613-623-3191 | TF: 800-267-7394

For a complete listing of our global offices, visit:

[www.nylene.com/contactus](http://www.nylene.com/contactus)

[www.nylene.com](http://www.nylene.com) | [info@nylene.com](mailto:info@nylene.com)

Copyright ©2019, Nylene. All rights reserved. Nylene is a designated trademark of Polymeric Resources Corporation.